

Makrolon 2458

General purpose grades / Low viscosity / High productivity Global grade; MVR 19 cm³/10 min; General purpose; Low viscosity; Easy release; Food contact quality; Good hydrolysis resistance; Injection molding; Available in transparent, translucent and opaque colors; Suitable for medical devices

ISO Shortname ISO 7391-PC,MR,49-18-9

Property	Test Condition	Unit	Standard	Value
Rheological properties				
C Melt volume-flow rate	300 °C; 1.2 kg	cm ³ /(10 min)	ISO 1133	19
C Molding shrinkage, parallel	60x60x2; 280 °C / MT 80 °C; 500 bar	%	ISO 294-4	0.6
C Molding shrinkage, normal	60x60x2; 280 °C / MT 80 °C; 500 bar	%	ISO 294-4	0.65
Molding shrinkage, parallel/normal	Value range based on general practical experience	%	acc. ISO 2577	0.5 - 0.7
Melt mass-flow rate	300 °C; 1.2 kg	g/(10 min)	ISO 1133	20

Mechanical properties (23 °C/50 % r. h.)

C Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	2400
C Yield stress	50 mm/min	MPa	ISO 527-1,-2	65
C Yield strain	50 mm/min	%	ISO 527-1,-2	6.0
C Nominal strain at break	50 mm/min	%	ISO 527-1,-2	> 50
Stress at break	50 mm/min	MPa	ISO 527-1,-2	65
Strain at break	50 mm/min	%	acc. ISO 527-1,-2	115
C Tensile creep modulus	1 h	MPa	ISO 899-1	2200
C Tensile creep modulus	1000 h	MPa	ISO 899-1	1900
Flexural modulus	2 mm/min	MPa	ISO 178	2350
Flexural strength	2 mm/min	MPa	ISO 178	98
Flexural strain at flexural strength	2 mm/min	%	ISO 178	7.0
Flexural stress at 3.5 % strain	2 mm/min	MPa	ISO 178	73
C Charpy impact strength	23 °C	kJ/m ²	ISO 179-1eU	N
C Charpy impact strength	-30 °C	kJ/m ²	ISO 179-1eU	N
Charpy notched impact strength	23 °C; 3 mm	kJ/m ²	acc. ISO 179-1eA	60P
Charpy notched impact strength	-30 °C; 3 mm	kJ/m ²	acc. ISO 179-1eA	12C
Izod notched impact strength	23 °C; 3.2 mm	kJ/m ²	acc. ISO 180-A	70P(C)
Izod notched impact strength	-30 °C; 3.2 mm	kJ/m ²	acc. ISO 180-A	12C
C Puncture maximum force	23 °C	N	ISO 6603-2	5200
C Puncture maximum force	-30 °C	N	ISO 6603-2	6200
C Puncture energy	23 °C	J	ISO 6603-2	55
C Puncture energy	-30 °C	J	ISO 6603-2	60
Ball indentation hardness		N/mm ²	ISO 2039-1	115

Thermal properties

C Glass transition temperature	10 °C/min	°C	ISO 11357-1,-2	145
C Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	125
C Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	138
C Vicat softening temperature	50 N; 50 °C/h	°C	ISO 306	145
Vicat softening temperature	50 N; 120 °C/h	°C	ISO 306	146
C Coefficient of linear thermal expansion, parallel	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.65
C Coefficient of linear thermal expansion, transverse	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.65
C Burning behavior UL 94 (1.6 mm) [UL recognition]	1.5 mm	Class	UL 94	V-2
C Burning behavior UL 94 [UL recognition]	2.6 mm	Class	UL 94	V-2
Burning behavior UL 94 [UL recognition]	0.75 mm	Class	UL 94	V-2
Burning behavior UL 94 [UL recognition]	2.7 mm	Class	UL 94	HB
Burning behavior UL 94 [UL recognition]	3.0 mm	Class	UL 94	HB
Burning behavior UL 94 [UL recognition]	6.0 mm	Class	UL 94	HB
C Oxygen index	Method A	%	ISO 4589-2	27
Thermal conductivity	23 °C	W/(m·K)	ISO 8302	0.20
Resistance to heat (ball pressure test)		°C	IEC 60695-10-2	135
Temperature index (Tensile strength)	20000 h; 1.5 mm	°C	IEC 60216-1	130
Halving interval (Tensile strength)	1.5 mm	°C	IEC 60216-1	7.9
Temperature index (Tensile impact strength)	20000 h; 1.5 mm	°C	IEC 60216-1	120

Makrolon 2458

Property	Test Condition	Unit	Standard	Value
Halving interval (Tensile impact strength)	1.5 mm	°C	IEC 60216-1	7.5
Temperature index (Electric strength)	20000 h; 1.5 mm	°C	IEC 60216-1	130
Halving interval (Electric strength)	1.5 mm	°C	IEC 60216-1	7.4
Relative temperature index (Tensile strength) [UL recognition]	1.5 mm	°C	UL 746B	125
Relative temperature index (Tensile impact strength) [UL recognition]	1.5 mm	°C	UL 746B	115
Relative temperature index (Electric strength) [UL recognition]	1.5 mm	°C	UL 746B	125
Glow wire test (GWFI)	1.0 mm	°C	IEC 60695-2-12	850
Glow wire test (GWFI)	1.5 mm	°C	IEC 60695-2-12	850
Glow wire test (GWFI)	2.0 mm	°C	IEC 60695-2-12	850
Glow wire test (GWFI)	3.0 mm	°C	IEC 60695-2-12	850
Application of flame from small burner	Method K and F; 2.0 mm	Class	DIN 53438-1,-3	K1, F1
Needle flame test	Method K; 1.5 mm	s	IEC 60695-2-2	5
Needle flame test	Method K; 2.0 mm	s	IEC 60695-2-2	5
Needle flame test	Method K; 3.0 mm	s	IEC 60695-2-2	10
Needle flame test	Method F; 1.5 mm	s	IEC 60695-2-2	60
Needle flame test	Method F; 2.0 mm	s	IEC 60695-2-2	120
Needle flame test	Method F; 3.0 mm	s	IEC 60695-2-2	120
Incandescent bar test		Rating	IEC 60707-BH	BH2/< 30 mm
Burning rate (US-FMVSS)	>=1.0 mm	mm/min	ISO 3795	passed
Flash ignition temperature	Procedure B	°C	ASTM D1929	470
Self ignition temperature	Procedure B	°C	ASTM D1929	540

Electrical properties (23 °C/50 % r. h.)

C Relative permittivity	100 Hz	-	IEC 60250	3.1
C Relative permittivity	1 MHz	-	IEC 60250	3.0
C Dissipation factor	100 Hz	10 ⁻⁴	IEC 60250	5
C Dissipation factor	1 MHz	10 ⁻⁴	IEC 60250	90
C Volume resistivity		Ohm·m	IEC 60093	1E14
C Surface resistivity		Ohm	IEC 60093	1E16
C Electric strength	1 mm	kV/mm	IEC 60243-1	33
C Comparative tracking index CTI	Solution A	Rating	IEC 60112	275
Comparative tracking index CTI M	Solution B	Rating	IEC 60112	125
Electrolytic corrosion		Rating	IEC 60426	A1

Other properties (23 °C)

C Water absorption (Saturation value)	Water at 23 °C	%	ISO 62	0.30
C Water absorption (Equilibrium value)	23 °C; 50 % RH	%	ISO 62	0.12
C Density		kg/m ³	ISO 1183	1200
Water permeation	23 °C; 85 % RH; 100 µm film	g/(m ² ·24 h)	ISO 15106-1	15
Gas permeation	Oxygen; 100 µm film	cm ³ /(m ² ·24 h·bar)	acc. ISO 2556	800
Gas permeation	Oxygen; 25.4 µm (1 mil) film	cm ³ /(m ² ·24 h·bar)	acc. ISO 2556	3150
Gas permeation	Nitrogen; 100 µm film	cm ³ /(m ² ·24 h·bar)	acc. ISO 2556	160
Gas permeation	Nitrogen; 25.4 µm (1 mil) film	cm ³ /(m ² ·24 h·bar)	acc. ISO 2556	630
Gas permeation	Carbon dioxide; 100 µm film	cm ³ /(m ² ·24 h·bar)	acc. ISO 2556	4800
Gas permeation	Carbon dioxide; 25.4 µm (1 mil) film	cm ³ /(m ² ·24 h·bar)	acc. ISO 2556	18900
Bulk density	Pellets	kg/m ³	ISO 60	660

Material specific properties

C Viscosity number		cm ³ /g	ISO 1628-4	51
Refractive index	Procedure A	-	ISO 489	1.586
Haze for transparent materials	3 mm	%	ISO 14782	< 0.8
Luminous transmittance (clear transparent materials)	1 mm	%	ISO 13468-2	89
C Luminous transmittance (clear transparent materials)	2 mm	%	ISO 13468-2	89
Luminous transmittance (clear transparent materials)	3 mm	%	ISO 13468-2	88
Luminous transmittance (clear transparent materials)	4 mm	%	ISO 13468-2	87

Processing conditions for test specimens

C Injection molding-Melt temperature		°C	ISO 294	280
C Injection molding-Mold temperature		°C	ISO 294	80
C Injection molding-Injection velocity		mm/s	ISO 294	200



Makrolon 2458

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.



Makrolon 2458

Disclaimer

Disclaimer for Sales products

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Test values

Unless specified to the contrary, the values given have been established on standardised test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and the colouring.

Medical products

**Only Bayer plastics which fulfil the test requirements of ISO 10 993-1 may be used for medical articles which come within the scope of this standard. Applications involving long-term contact for which Bayer plastics are not intended are exceptions. However, the biocompatibility tests which we perform according to this standard do not cover the following ranges of application for medical articles manufactured from our material: Long-term use over 30 days, particularly use as (cosmetic or reconstructive) implant Long-term contact over 30 days with endogenous substances (blood, tissue, dentin, other body fluids) Multiple use for medical applications Therefore Bayer plastics should not be used for long-term applications or with long-term contact. Use of recycled material and incompatible additives Our test results for biocompatibility do not apply to the use of recycled materials or the use of other additional material components in the finished product. Responsibility of the manufacturer of the medical article The use of our material outside the above-mentioned test scope of ISO 10 993-1 occurs exclusively on the responsibility of the processor of our material and the manufacturer of the finished product. As regards the production conditions of the processor of our material which are not known to us, it is the responsibility of the processor to ascertain the suitability of our materials in the finished product in terms of directives and statutes to be observed. The suitability of our materials also depends on the ambient conditions (see below) for the finished product. Chemical compatibility, temperature, design of the medical article, method of sterilization, internal stress within the finished article, and external stress all influence suitability, and are therefore the responsibility of the processor and the manufacturer of the finished product. Multiple-use of medical articles Medical articles which are intended for single use and which were manufactured from Bayer plastic are not suitable for multiple use. If the medical article was manufactured for multiple use, it is the responsibility of the manufacturer of the finished product to determine an appropriate number of times it may be used, by determining and evaluating the conditions of sterilization and final use. Appropriate warnings and instructions must be given to the final user. Sterilization The use of various methods of sterilization and the permitted number of sterilization cycles for a medical article which is made from our materials depend on the design of the parts, the processing parameters, the sterilization temperature and the chemical environment. Therefore the manufacturer must determine and evaluate the most suitable method of sterilization (and if applicable the permitted number of sterilization cycles) for each medical article. Appropriate instructions and warnings must be given to the final user.

Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.

Publisher: Business Development Plastics

Bayer MaterialScience AG,

D-51368 Leverkusen,

www.bayermaterialscience.com