



CHI MEI CORPORATION

59-1 SAN CHIA, JEN TE, TAINAN COUNTY, TAIWAN R.O.C. TEL: 886-6-266-5000, FAX: 886-6-266-5555~7

High Heat ABS, POLYLAC[®] PA-777B

V1W

Typical Characteristics

Properties	Test Method	Test Condition	Unit	PA-777B
Tensile Strength	ASTM D638	1/8", 6 mm/min	Kg/cm ² (lb/in ²)	430(6100)
Tensile Elongation	ASTM D638	1/8", 6 mm/min	%	15
Flexural Strength	ASTM D790	1/4", 2.8 mm/min	Kg/cm ² (lb/in ²)	700(9920)
Flexural Modulus	ASTM D790	1/4", 2.8 mm/min	Kg/cm ² (lb/in ²)	24000(340000)
Izod Impact Strength (Notched)	ASTM D256	1/4", 23°C	Kg-cm/cm(ft-lb/in)	20(3.7)
		1/8", 23°C	Kg-cm/cm(ft-lb/in)	23(4.3)
Melt Flow Index	ASTM D1238	220°C, 10Kg	g/10min	6.5
Hardness	ASTM D785	1/2"	R Scale	112
Specific Gravity	ASTM D792	23°C	g/cm ³	1.03
Vicat Softening Temp	ASTM D1525	1/8", 50°C /hr	°C (°F)	115(239)
H.D.T	ASTM D648	1/4", 120°C /hr	°C (°F)	107(225) 97(206)
Annealed(85°C X8hr) Unannealed				
Flammability	UL 94	-	-	1/16"HB

The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere.

For further information, please contact your local agent or fax to Chi Mei Technical Services Dept. at 886-6-2665555