

PROPERTY INFORMATION

KOLON INDUSTRIES INC

KOPEL[®]

POLYESTER ELASTOMER RESIN

KP3363

GENERAL GRADE 63D

PROPERTY	ASTM METHOD	UNIT			VALUE		
MISCELLANEOUS							
SPECIFIC GRAVITY	D792				1.23		
HARDNESS, DUROMETER	D2240	D-TYPE			65		
MELT INDEX	D1238	g / 10 min			20		
WATER ABSORPTION	D570	%			0.3		
MOLD SHRINKAGE	D955	%			1.3		
THERMAL							
MELTING POINT	DSC	°C	°F	210	410		
HEAT DISTORTION TEMPERATURE	D648						
		°C	°F	120	248		
SOLENOID BRITTLE POINT	D746	°C	°F	< -70	< -94		
FLAMMABILITY	UL94				HB		
MECHANICAL							
TENSILE STRENGTH	D638	kgf/cm ²	Mpa	psi	380	37	5,403
TENSILE ELOGATION	D638	%			550		
FLEXURAL MODULUS	D790	kgf/cm ²	Mpa	psi	3,000	294	42,659
IZOD NOTCHED IMPACT STRENGTH	D256						
		kgcm/cm	J/m	ft.lb/in	N/B ¹⁾	N/B	N/B
		kgcm/cm	J/m	ft.lb/in	8.4	82	1.55
ABRASION RESISTANCE CS-17 WHEEL	D1044	mg / 10 ³ cycles			7.0		
RESILIENCE		%			43		

1) N/B : NOT BREAKBLE

The information provided on our present state of knowledge and is estimated by Kolon Industries Inc. The listed values should be used for referential purposed only. This information should not be used as guranteed specification limits.

Kolon industries Inc assumes no warranty, no obligations or liability of, express or implied aas to the accuracy or compeltteness thereof, or any other nature regarding designs, products, or information may be used without infringing the intellectual property rights of others. All such advice is given and accepted at buyer's risk.

KOLON INDUSTRIES INC, PLASTIC DIVISION SINCE 1957
HEAD OFFICE TEL : +822-3677-3611~14 FAX: +822-3677-3557~8
R & D CENTER TEL : +82-54-469-3810,3872~3 FAX : +82-54-496-6113
GUMI PLANT TEL : +82-54-469-3587 FAX : +82-54-469-3177