



# CHI MEI CORPORATION

59-1 SAN CHIA, JEN TE, TAINAN COUNTY, TAIWAN R.O.C. TEL: 886-6-266-5000, FAX: 886-6-266-5555-7

## TPE, KIBITON<sup>®</sup> PB-575

August 19, 2004 VIW

### Typical Characteristic

Properties	Test Method	Test Condition	Unit	PB-575
BD/SM Ratio	ASTM D1416	-	%	60/40
Volatile matter	ASTM D1416	-	wt%	0.6
Ash Content	ASTM D1416	-	wt%	0.2
Oil Content	ASTM D1416	-	phr	50
Melt Flow Index	ASTM D1238	200 ,5Kg	g/10min	6.0
Melt Flow Index	ASTM D1238	190 ,5Kg	g/10min	4.5
Hardness	ASTM D2240	-	Shore A	63
Specific Gravity	ASTM D792	23	-	0.94
Appearance	-	-	-	Foam Pellet
Bale Weight	-	-	Kg	20

The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere.

For further information, please contact your local agent or fax to Chi Mei Technical Services Dept. at 886-6-2665555